

Evolving Gold Complete Assays
14-Apr-09

Intervals reported in this table all meet the following criteria:

- 1) All are at least 6 m long with the exception of select sub-intervals with notably higher grades.
- 2) Intervals were selected using a cut-off grade of 0.25 gpt and are calculated using a weighted average of individual samples.
- 3) Reported intervals allow for the inclusion of sub-intervals of up to 6 m in length grading less than cutoff.
- 4) Aggregate composites are weighted averages of intervals highlighted in yellow.
- 5) High grade intervals are highlighted in red.

Antelope Basin

Hole	From (m)	To (m)	Interval (m)	Initial Assay g/t Gold	Metallic Screen Assay g/t Gold	Interval (ft)	Initial Assay oz/ton Gold	Metallic Screen Assay oz/ton Gold
RSC-1	22.9	160.0	137.1	0.38	0.46	450.0	0.011	0.013
inc	143.2	160.0	16.8	0.61	0.69	55.0	0.018	0.020
	169.2	205.7	36.5	1.46	1.48	120.0	0.043	0.043
inc	170.7	184.4	13.7	2.49	2.46	45.0	0.073	0.072
inc	172.1	181.4	9.3	3.21	3.47	30.4	0.094	0.101
	Aggregate composite		173.6	0.61	0.67	570.0	0.018	0.020

North Stock

Hole	From (m)	To (m)	Interval (m)	Initial Assay g/t Gold	Metallic Screen Assay g/t Gold	Interval (ft)	Initial Assay oz/ton Gold	Metallic Screen Assay oz/ton Gold
RSC-3	149.3	295.6	146.3	2.48	2.92	480.0	0.072	0.085
inc	149.3	198.1	48.8	2.22	2.40	160.0	0.065	0.070
inc	211.8	239.2	27.4	5.67	5.98	90.0	0.166	0.175
inc	233.2	238.4	5.2	13.83	15.15	17.0	0.404	0.442
inc	243.8	257.8	14.0	4.65	8.15	46.0	0.136	0.238
inc	249.9	257.8	7.9	7.87	13.95	26.0	0.230	0.407
inc	269.7	295.6	25.9	1.01	0.95	85.0	0.029	0.028
inc	342.9	416.1	73.2	0.76	0.90	240.0	0.022	0.026

RSC-4	202.7	228.6	25.9	*	0.84	85.0	*	0.025
inc	208.5	228.6	20.1	0.89	0.98	66.0	0.026	0.029
inc	208.5	213.1	4.6	2.54	1.41	15.0	0.074	0.041
	243.8	294.1	50.3	*	0.76	165.0	*	0.022
	251.2	294.1	42.9	0.81	0.83	141.0	0.024	0.024
inc	251.2	278.9	27.7	1.06	1.11	91.0	0.031	0.032
inc	257.6	263.7	6.1	2.01	1.55	20.0	0.059	0.045
	388.6	403.9	15.3	0.97	0.88	50.0	0.028	0.026
inc	396.2	402.3	6.1	1.80	1.23	20.0	0.053	0.036
ends in mineralization	Aggregate composite		134.4	0.81	0.81	441.0	0.024	0.024

RSC-5	109.7	163.1	53.4	1.14	1.14	175.0	0.033	0.033
inc	109.7	133.4	23.7	1.47	1.34	78.0	0.043	0.039
inc	152.4	163.1	10.7	2.45	2.51	35.0	0.072	0.073
inc	158.5	163.1	4.6	4.29	4.65	15.0	0.125	0.136
	268.5	330.7	62.2	0.64	0.64	204.0	0.019	0.019
inc	306.3	324.6	18.3	1.16	1.15	60.0	0.034	0.034
	370.3	467.9	97.6	0.47	0.47	320.0	0.014	0.014
inc	420.6	428.2	7.6	*	1.69	25.0	*	0.049
	486.2	547.1	60.9	0.50	0.48	200.0	0.015	0.014
inc	504.4	544.1	39.7	*	0.64	130.0	*	0.019
inc	509.0	522.7	13.7	1.09	0.83	45.0	0.032	0.024
	Aggregate composite		274.1	0.65	0.64	899.0	0.019	0.019

RSC-6	59.4	83.8	24.4	*	0.78	80.0	*	0.023
inc	59.4	74.7	15.3	0.85	0.91	50.0	0.025	0.027
	135.6	219.9	84.3	0.95	1.03	276.4	0.028	0.030
inc	135.6	181.4	45.8	1.45	1.47	150.4	0.042	0.043
inc	173.7	178.3	4.6	8.87	8.73	15.0	0.259	0.255
	190.5	219.9	29.4	*	0.55	96.4	*	0.016
	274.3	310.9	36.6	*	0.71	120.0	*	0.021
inc	280.4	310.9	30.5	0.59	0.78	100.0	0.017	0.023
	338.3	417.6	79.3	0.47	0.48	260.0	0.014	0.014
inc	368.8	387.1	18.3	1.16	1.16	60.0	0.034	0.034
inc	378.0	384.1	6.1	2.20	2.32	20.0	0.064	0.068
	446.5	544.7	98.2	0.92	1.10	322.0	0.027	0.032
inc	483.1	487.7	4.6	2.15	1.71	15.0	0.063	0.050
inc	530.4	544.7	14.3	2.18	2.21	47.0	0.064	0.065
inc	541.0	544.7	3.7	4.01	4.00	12.0	0.117	0.117
ends in mineralization	Aggregate composite		352.2	0.84	0.84	1154.8	0.024	0.024

RSC-7	105.2	236.2	131.0	2.74	2.84	430.0	0.080	0.083
inc	134.1	170.7	36.6	3.70	3.82	120.0	0.108	0.112
inc	160.0	169.2	9.2	8.11	7.85	30.0	0.237	0.229
inc	185.9	219.5	33.6	3.91	4.15	110.0	0.114	0.121
inc	189.0	195.1	6.1	7.56	7.72	20.0	0.221	0.225
	236.2	411.5	175.3	0.37	0.61	575.0	0.011	0.018
	451.1	467.9	16.8	*	0.49	55.0	*	0.014
	542.5	554.1	11.6	0.90	0.96	38.0	0.026	0.028
inc	551.7	554.1	2.4	1.74	1.82	8.0	0.051	0.053
inc	553.2	554.1	0.9	2.58	2.68	3.0	0.075	0.078
ends in mineralization	Aggregate composite		203.7	0.62	0.62	668.0	0.018	0.018

RSC-8	129.5	146.3	16.8	0.32	No metallic screen assays	55.0	0.009	No metallic screen assays
	239.3	249.9	10.6	0.28	No metallic screen assays	35.0	0.008	No metallic screen assays
	Aggregate composite		27.4	0.30		90.0	0.009	

RSC-9	18.3	53.3	35.0	*	0.47	115.0	*	0.014
inc	24.4	53.3	28.9	0.45	0.51	95.0	0.013	0.015
	94.5	274.3	179.8	0.64	0.71	580.0	0.019	0.021
inc	192.0	210.3	18.3	*	1.89	60.0	*	0.055
	402.3	462.7	60.4	0.34	0.29	198.0	0.010	0.008
ends in mineralization	Aggregate composite		275.2	0.59	0.59	903.0	0.017	0.017

RSC-10	42.7	64.0	21.3	0.39	No metallic screen assays	70.0	0.011	No metallic screen assays
failed hole								
ends in mineralization								

RSC-11	109.7	123.6	13.9	*	0.71	45.0	*	0.021
	271.3	342.9	71.6	0.33	0.37	235.0	0.010	0.011
	Aggregate composite		85.5	0.43	0.43	280.0	0.012	0.012

RSC-12	13.7	167.6	153.9	1.09	1.21	505.0	0.032	0.035
inc	53.3	73.2	19.9	2.03	2.11	65.0	0.059	0.062
inc	94.5	109.7	15.2	2.03	2.19	50.0	0.059	0.064
inc	161.5	167.6	6.1	2.03	2.46	20.0	0.059	0.072
	176.8	196.6	19.8	0.61	1.04	65.0	0.018	0.030
	213.4	257.6	44.2	1.09	1.20	145.0	0.032	0.035
inc	227.1	234.7	7.6	2.09	2.16	25.0	0.061	0.063
inc	237.7	244.5	6.8	2.04	1.90	22.0	0.060	0.055
	330.7	374.9	44.2	0.33	0.40	145.0	0.010	0.012
	382.5	426.7	44.2	0.97	0.98	145.0	0.028	0.029
inc	410.0	423.7	13.7	2.06	2.07	45.0	0.060	0.060
	455.7	480.7	25.0	0.95	0.98	115.0	0.028	0.029
	524.3	542.6	18.3	0.36	No metallic screen assays	60.0	0.011	No metallic screen assays
	Aggregate composite		359.6	0.90	1.01	1180.0	0.026	0.029

RSC-13	19.8	39.6	19.8	0.45	No metallic screen assays	65.0	0.013	No metallic screen assays
	51.8	76.2	24.4	0.58	No metallic screen assays	80.0	0.017	No metallic screen assays
	91.4	129.5	38.1	0.40	No metallic screen assays	125.0	0.012	No metallic screen assays
	237.7	286.5	48.8	0.37	No metallic screen assays	160.0	0.011	No metallic screen assays
	Aggregate composite		131.1	0.43		430.0	0.013	

RSC-14	7.6	42.7	35.1	0.68	0.71	115.0	0.020	0.021
inc	22.9	29.0	6.1	2.00	2.05	20.0	0.058	0.060
	292.6	304.8	12.2	0.39	No metallic screen assays	40.0	0.011	No metallic screen assays
	323.1	341.4	18.3	0.31	No metallic screen assays	60.0	0.009	No metallic screen assays
	428.2	438.9	10.7	0.45	No metallic screen assays	35.0	0.013	No metallic screen assays
	451.1	459.4	8.3	0.30	No metallic screen assays	27.0	0.009	No metallic screen assays
ends in mineralization	Aggregate composite		84.6	0.49		162.0	0.014	

RSC-15	12.2	32.0	19.8	0.32	No metallic screen assays	65.0	0.010	No metallic screen assays
	41.1	89.9	48.8	0.80	0.96	160.0	0.023	0.028
	359.7	373.4	13.7	0.32	No metallic screen assays	45.0	0.010	No metallic screen assays
ends in mineralization	Aggregate composite		82.3	0.60		270.0	0.018	

Yellow = intervals making up aggregate composites
Red = high grade intervals